## 200XT COLOUR RANGE

Nearest BS colour numbers are indicated



Expected time to first full repainting		Wall Cladding		Roof Cladding
Standard Colours	Nearest BS ref <sup>2</sup>	Inland	Marine <sup>3</sup>	
Jade	14C37	25 years	20 years	20 years
Country Green	-	25 years	20 years	20 years
Juniper Green	12B29	25 years	20 years	20 years
Slate Blue	18B29	25 years	20 years	20 years
Willow	12B17	30 years	25 years	25 years
Moorland Green	12B21	30 years	25 years	25 years
Forest Green	RAL6002	25 years	20 years	20 years
Olive Green	12B27	30 years	25 years	25 years
lvory	RAL9002	30 years	25 years	25 years
Mushroom	10B19	30 years	25 years	25 years
New Grey	10B23	30 years	25 years	25 years
Merlin Grey	18B25	30 years	25 years	25 years
White <sup>1</sup>	00E55	30 years	25 years	25 years
Pigeon Grey	18B17	30 years	25 years	25 years
Goosewing Grey	10A05	30 years	25 years	25 years
Black	00E53	25 years	20 years	20 years
New Red	04D44	25 years	20 years	20 years
Buttermilk	10C31	30 years	25 years	25 years
Bamboo	08C35	30 years	25 years	25 years
Vandyke Brown	08B29	25 years	20 years	20 years
Terracotta	04C39	25 years	20 years	20 years
Wedgewood Blue	18C37	25 years	20 years	20 years
Ocean Blue	18C39	25 years	20 years	20 years
Pacific Blue	18E58	25 years	20 years	20 years
Tangerine Orange	06E53	25 years	20 years	20 years
Poppy Red	04E53	25 years	20 years	20 years
Navy	RAL5003	25 years	20 years	20 years
Cornflower Blue	18E53	25 years	20 years	20 years

<sup>1</sup> Where matching colour matching on White (00E55) is critical, it is important that the material is purchased from the same production

Substrate: 200XT Exterior is available on Hot Dipped Zinc Galvanised Steel to BS EN 10142:1991

Overpainting of the underside of lapped edges, together with the exposed cut edge, may be advisable for some severe industrial, coastal and marine environments; as in some conditions the substrate properties are included in the total sheet life.

The standard reverse coating is specifically designed for bonding most injected insulation foams and laminating of slab.

Certain colours, in specific instances, may well have a longer period to first maintenance than shown in the table above.



<sup>&</sup>lt;sup>2</sup> These numbers are for guidance only, as the colours vary slightly from British Standard.

<sup>&</sup>lt;sup>3</sup> Within 1 1/2 miles of shoreline.